

Datasheet revision 1.1

www.chipquik.com

Electronics Grade Silicone Adhesive Sealant (Clear) 20g Squeeze Tube

Product Highlights

Safe for use with Electronics Seals, Bonds, Encapsulates Resistant to Various Chemicals and Oils Non-Corrosive, Non-Conductive Flexible, Durable, Non-Degrading Withstands Moisture, Vibration, Abrasion



Common Uses

Protecting, Sealing and Insulating Corrosion Sensitive Electronic Components and Electrical Materials. OEM Commercial and Industrial Manufacturing for Flexible Permanent Bonding and Sealing.

Instructions

Surfaces should be clean and dry. Unscrew cap, cut the tip off. If tooling is required, do so within the first 10 minutes after dispensing. Apply the silicone to surfaces and remove the excess silicone after tooling with a dry clean cloth. Allow the silicone to cure completely. At room temperature, 25°C (77°F), and 50% relative humidity, the silicone will skin in 10 minutes and fully cure in 24 hours (1/8" bead). The silicone will reach its maximum adhesion in 7 days. Higher humidity accelerates curing.

Specifications

Meets and Exceeds:	ASTM C920, UL Recognized
VOC:	VOC Compliant (<3%), Low Odor
Operating Temperature Range:	-57°C to +204°C (-70°F to +400°F)
Curing Time:	10 min (skin), 24 hours (full cure), 7 days (max adhesion)
Color:	Clear
Size:	20g squeeze tube
Shore A Hardness:	30
Tensile Strength:	250psi
Tear Strength:	30psi
Elongation:	400%
Dielectric Strength:	460 V/mil (18 kV/mm)
Operating Temperature Range: Curing Time: Color: Size: Shore A Hardness: Tensile Strength: Tear Strength: Elongation:	-57°C to +204°C (-70°F to +400°F) 10 min (skin), 24 hours (full cure), 7 days (max adhesion) Clear 20g squeeze tube 30 250psi 30psi 400%

Storage and Handling

Store refrigerated or at room temperature 3-25°C (37-77°F).

Shelf Life >36 months

Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.